



Customer Specification Sol-Vex #37-145

PRODUCT NOMENCLATURE

Manufacturing Glove Code: **#37-145**
Manufacturing Glove Name: **Sol-Vex**
Marketing Glove ASPN Code(s): **(6)-117071 (7)-117073 (8)-117074 (9)-117075 (10)-117076 (11)-117077**

PRODUCT DESCRIPTION

Product Classification:	Chemical Resistant (Unsupported)	Lining:	Unlined, Chlorinated
Exterior Color:	Green		
Former Pattern Style:	Sandpatch	Exterior Finish:	Chlorinated
Coating Composition:	Nitrile	Cuff Finish:	Straight (unpinked)
Available Sizes:	6, 7, 8, 9, 10 and 11	Printing:	Inkjet Black
Packaging:	12 Pairs per inner bag 12 Inner bags per case (144 Pairs)	Length:	12.75 in. (324 mm) Minimum

OUTSTANDING CHARACTERISTICS & APPLICATIONS

- ◆ Provides excellent snag, puncture, abrasion and cut resistance.
- ◆ Outstanding resistance to a wide range of chemicals, including aromatic solvents, petroleum solvents and animal fats.
- ◆ **APPLICATIONS:** *Chemical Processing, Oil Refining, Petrochemicals, Food Processing (red meat, poultry, vegetables, fruit, dairy and canning), Aerospace and Automotive Degreasing, Automotive Painting and Assembly, Machining Operations, Metal Fabrication, Graphic Arts, Furniture Manufacturing, Electronics (semiconductors & circuit boards)*

REGULATORY COMPLIANCES

- ◆ Complies with FDA regulation 21 CFR 177.2600 for food contact applications.

TYPICAL PERFORMANCE VALUES

◆ Thickness	11 ± 2 mils (0.28 ± 0.05 mm)	ASTM D 412
◆ Tensile Strength	> 3000 psi (> 20.7 Mpa)	ASTM D 412
◆ 300% Modulus	2700 psi (18.6 Mpa) Maximum	ASTM D 412
◆ Elongation @ Break	> 350%	ASTM D 412
◆ Abrasion Resistance	Performance Level 4 (> 8000 cycles)	EN 388
◆ Puncture Resistance	Performance Level 2 (65 - 75 newtons)	EN 388
◆ Chemical Resistance	See Ansell 6 th Edition Chemical Resistance Guide	ASTM F 739

DEFECTS

DEFINITIONS: **Major Defects** are imperfections which *may result* in the failure of the glove to perform it's intended purpose, cause user discomfort or be cosmetically objectionable. **(AQL- 1.0%)**
Minor Defects may cause user discomfort or be cosmetically objectionable. **(AQL- 2.5%)**

MAJOR DEFECTS: **Holes/Splits/Tears/Thin Spots/No Flock/Porosity**

MINOR DEFECTS: **Blisters/Runs/Lumps/Webs/Stains/Creases/Poor Pinking/Insufficient Flock/Ink Smear**

GENERAL INFORMATION

SHELF LIFE: Five (5) years in cool, covered conditions. Extended exposure to direct sunlight or excessive heat will reduce shelf life and result in fading, discoloration and cracking.

NOTE: *This product contains NO natural rubber latex.*

Originator: Paul McMorrow

Date: 02/06/01

Revised By:

Date:

Revision #:

NEITHER THIS NOR ANY STATEMENT MADE BY OR ON BEHALF OF ANSELL HEREIN IS A WARRANTY THAT ANY PRODUCT IS FIT FOR A PARTICULAR PURPOSE, AND ANSELL SHALL NOT BE LIABLE TO ANYONE WITH RESPECT TO THIS INFORMATION.

This document is the property of Ansell and the information contained herein is proprietary to Ansell.